Micromagnetic simulations of the size dependence of the Curie temperature in ferromagnetic nanowires and nanolayers

 $\begin{array}{ccc} \mbox{Clémentine Courtès}^{1,2} & \mbox{Matthieu Boileau}^{1,2} & \mbox{Raphaël Côte}^{1,3} \\ \mbox{Paul-Antoine Hervieux}^4 & \mbox{Giovanni Manfredi}^4 \end{array}$

January 25, 2024

Abstract

We solve the Landau-Lifshitz-Gilbert equation in the finite-temperature regime, where thermal fluctuations are modeled by a random magnetic field whose variance is proportional to the temperature. By rescaling the temperature proportionally to the computational cell size Δx $(T \to T \Delta x/a_{\text{eff}})$, where a_{eff} is the lattice constant) [M. B. Hahn, J. Phys. Comm., 3:075009, 2019], we obtain Curie temperatures T_{C} that are in line with the experimental values for cobalt, iron and nickel. For finite-sized objects such as nanowires (1D) and nanolayers (2D), the Curie temperature varies with the smallest size d of the system. We show that the difference between the computed finite-size T_{C} and the bulk T_{C} follows a power-law of the type: $(\xi_0/d)^{\lambda}$, where ξ_0 is the correlation length at zero temperature, and λ is a critical exponent. We obtain values of ξ_0 in the nanometer range, also in accordance with other simulations and experiments. The computed critical exponent is close to $\lambda = 2$ for all considered materials and geometries. This is the expected result for a mean-field approach, but slightly larger than the values observed experimentally.

Contents

Introduction

T	11101		2		
2	2 Micromagnetic model at finite temperature				
	2.1	Effective magnetic field $\boldsymbol{H}_{\mathrm{eff}}$	5		
	2.2	Thermal fluctuations	6		
	2.3	Temperature scaling with the computational cell size	7		

n

8

3 Computational method

 $^{^1 \}rm University$ of Strasbourg CNRS, IRMA UMR 7501, F-67000 Strasbourg, France $^2 \rm INRIA$ Nancy Grand-Est, TONUS Team, France

³University of Strasbourg Institute for Advanced Study, F-67000 Strasbourg, France

⁴University of Strasbourg, CNRS, IPCMS UMR 7504, F-67000 Strasbourg, France

11
11
12
14
17
17
17
20
24

Keywords: Micromagnetism, Landau-Lifshitz-Gilbert equation, Curie temperature, nanowire, nanolayer, size effect.

1 Introduction

Interest in nano-scale ferromagnetic objects (nanowires, nanolayers, etc.) has grown dramatically in recent years, as these objects are integrated into many current devices with the aim of storing, reading and writing digital information. Hence, there is a growing need for accurate numerical simulations capable of predicting the behaviour of such objects, and possibly predict new properties and features. Computational models of ferromagnetic materials can be roughly divided into two families. On the one hand, atomistic models such as VAMPIRE [8] describe the magnetic interactions microscopically, at the natural atomic length scale of the material. Although in principle very accurate, they demand a considerable computational cost and are thus limited to relatively small systems.

In contrast, micromagnetism describes the structure and dynamics of a ferromagnetic object at an intermediate mesoscopic scale, averaging over a large number of atoms. Micromagnetic codes, based on the Landau-Lifshitz-Gilbert (LLG) equation, describe the dynamics of the average magnetic moment m(t, x), which is a continuous function of the spatial coordinate x. Notable projects in computational micromagnetism are the OOMMF project [7] (Object Oriented MicroMagnetic Framework) for the development of a public micromagnetic program in C++, the mumax3 project [30], a GPU-accelerated micromagnetic simulation program, or else the tetmag project, a 3D micromagnetic finite-element simulation software [13].

Here, we will adopt the micromagnetic approach (LLG equation) to study the influence of the temperature on some fundamental properties of both 1D (nanowires) and 2D (nanolayers) ferromagnetic nano-objects, for which thermal effects may become important. In order to model thermal fluctuations in the context of micromagnetics, in 1963 Brown [3] proposed to add a stochastic term

to the LLG equation, in the form of a randomly fluctuating magnetic field with zero mean and variance that is proportional to the temperature.

However, the Brown method suffers from a fundamental problem: while the LLG equation is valid at a mesoscopic scale and the corresponding magnetic moment $\boldsymbol{m}(t, \boldsymbol{x})$ represents an average over many atomic spins, thermal fluctuations occur at the atomic level. Hence, one is mixing two different levels of descriptions in the same LLG equation: the mesoscopic level for the deterministic terms, and the microscopic level for the stochastic terms. Then, if applied without further corrections, this procedure entails that temperature effects (for instance, the numerically-calculated Curie temperature) depend on the computational cell, which is obviously a spurious result.

Indeed, the computational cell size Δx is noticeably larger than the physical lattice constant a_{eff} . Thermal fluctuations occur at the length scale a_{eff} , but are necessarily implemented at the scale Δx in the micromagnetic codes. This induces an error in the computed properties, in particular near the Curie temperature T_{C} , which can be overestimated by one order of magnitude or more [11].

In order to mitigate this spurious effect, several strategies have been proposed. In one approach [15, 16], the magnetization at saturation M_s is scaled with the temperature and the computational cell size, using a Bloch-like law that is similar to the well-known temperature dependence of M_s . By comparing the micromagnetic results to those obtained with an atomistic model, the authors of [15, 16] obtain a difference of less than 1% in the estimation of the equilibrium magnetization, for a temperature $T = 0.38 T_{\rm C}$ and a computational cell size $\Delta x = 1.5$ nm.

Another approach [11] consists in defining a rescaled temperature to take into account the fact that thermal averages (coarse graining) are performed on a computational cell that is larger than the lattice constant. In particular, the effective exchange constant varies with the size of the coarsegraining block, and this dependence should be taken into account. Grinstein and Koch [11] used renormalization-group techniques to unravel this dependence. In the same spirit, Hahn [12] proposed a simple scaling law between the physical temperature and a "numerical" temperature to be used in the micromagnetic code, which depends on the ratio between the computational cell size and the lattice constant. This method was tested for nickel, cobalt and iron objects using the OOMMF code [7], and yielded Curie temperature that were virtually independent on the computational cell and very close to the experimental values.

A possible limitation of the LLG approach is that the amplitude of the local magnetic moment $|\boldsymbol{m}(t, \boldsymbol{x})|$ remains constant in time, which is not necessarily true at high temperatures, notably near $T_{\rm C}$. Chubykalo-Fesenko et al. [4] have investigated this issue using an atomistic time-dependent model and indeed they found that the modulus of the magnetization varies in time (see figure 1 in [4]). However, this variation is limited to a dip during an initial transient, after which $|\boldsymbol{m}(t, \boldsymbol{x})|$ recovers approximately its initial value. As our results are obtained by taking time-averages at longer times, this variation should not be too significant. But indeed, when studying transient phenomena, it may be necessary to take this effect into account, for instance by using a Landau-Lifshitz-Bloch approach, as suggested in [4, 2].

In the present work, we adopt Hahn's method to model thermal effects [12] and use it to study the dependence of the magnetization law (in particular the Curie temperature) with the size of the system under consideration. We will focus on two nano-objects, namely one-dimensional (1D) nanowires and 2D nanolayers. Theoretical considerations [9] indicate that the Curie temperature follows a power-law of the type:

$$\frac{T_{\rm C}(\infty) - T_{\rm C}(d)}{T_{\rm C}(\infty)} = \left(\frac{\xi_0}{d}\right)^{\lambda},$$

where d is the smallest size of the system, $T_{\rm C}(\infty)$ and $T_{\rm C}(d)$ are the Curie temperatures of the bulk and of the finite system respectively, ξ_0 is the correlation length at zero temperature, and λ is the critical exponent. The main purpose of this work will be to validate the above law and obtain the exponent and the correlation length from micromagnetic simulations with thermal effects.

From an experimental point of view, several works considered this problem. Early studies on thin nickel films, cobalt films and Co₁Ni₉ alloys yielded critical exponents $\lambda = 1.25$, 1.34 and 1.39, respectively [28, 14], while measurements on nickel films [21] revealed an exponent $\lambda = 1.4$. Later work on nickel nanowires [29], with diameters ranging from 30nm to 500nm, yielded $\xi_0 = 2.2$ nm and $\lambda = 0.94$. More recent works [33, 31] mention larger values for the exponent, up to $\lambda = 2.8$.

On the theory front, statistical estimations based on a first-principles-based Monte Carlo approach yielded a critical exponent $\lambda = 1.47$ for Pb(Zr_{0.5} Ti_{0.5} O₃) (PZT) thin films [1]. Similar values were obtained using other approaches [32]. These exponents should be compared to the theoretical values predicted by the 3D Heisenberg and Ising models (respectively, $\lambda = 1.4$ and $\lambda = 1.58$). In contrast, an atomistic mean-field model [25] yielded larger values, close to $\lambda = 2$ (range: $\lambda \in [1.82 - 2.17]$), for magnetite nanoparticles of different shapes and sizes. As we shall see, our own work suggests a critical exponent close to $\lambda \approx 2$, for both nanowires (1D) and nanolayers (2D). The observed correlation length is found to be $\xi_0 \approx 3$ nm for nanowires and $\xi_0 \approx 1.6$ nm for nanolayers.

We further note that our results are obtained using a time-dependent model, in contrast to statistical and Monte Carlo approaches used in other studies [1]. In other words, we solve the time-dependent LLG equation with thermal effects and, once a fluctuating equilibrium is reached, we measure the relevant magnetic properties by performing ensemble averages over many realizations and/or time averages over a certain duration. This approach is less computationally expensive than fully atomistic simulations. In addition, it is amenable to investigating the *dynamical* properties of magnetism, such as the propagation of domain walls and other transient effects, which will make the object of future work. Here, we have used this time-dependence to show that statistical fluctuations explose near $T_{\rm C}$, confirming the presence of a phase transition at that temperature.

The present paper is organized as follows. Section 2 details the mathematical setting, namely the LLG equation at finite temperature. After recalling the various terms involved in the effective magnetic field in Sec. 2.1, the following subsections are devoted to the modelling of thermal effects through a stochastic magnetic field (Sec. 2.2) and to the implementation of the temperature scaling [12] (Sec. 2.3). Section 3 contains the details of the numerical scheme. Section 4 is devoted to the validation of the numerical code with several test cases (Sec. 4.1), clearly proving that the Curie temperature does not depend on the computational cell size or the time step (Sec. 4.2). The validity of the Bloch law (at low temperatures, $T \ll T_{\rm C}$) and Curie law (at $T \leq T_{\rm C}$) are also tested (Sec. 4.3). Finally, Section 5 contains the main results of this work, namely the size dependence of the Curie temperature for two types of nano-objects: 1D nanowires and 2D nanolayers. Conclusions are drawn in Section 6.

2 Micromagnetic model at finite temperature

The present numerical study focuses on a ferromagnetic domain modeled either as an infinite nanowire along the e_x axis, where (e_x, e_y, e_z) is the canonical orthonormal basis in \mathbb{R}^3 , or an infinite nanolayer in the (e_x, e_y) plane. For all times $t \geq 0$ and positions $x \in \mathbb{R}^3$, let $m(t, x) \in \mathbb{S}^2 = \{m \in \mathbb{R}^3, ||m|| = 1\}$ be the magnetic moment vector field normalized to the saturation magnetization M_s . Here, \mathbb{S}^2 is the unit sphere. The precession dynamics of m(t, x) is described by the Landau-Lifshitz-Gilbert (LLG) equation:

$$\frac{\partial \boldsymbol{m}}{\partial t} = -\gamma_0 \, \boldsymbol{m} \times \boldsymbol{H}_{\text{eff}} - \gamma_0 \alpha \, \boldsymbol{m} \times (\boldsymbol{m} \times \boldsymbol{H}_{\text{eff}}) \,, \tag{1}$$

where $\boldsymbol{H}_{\text{eff}}$ is the effective magnetic field. Here, $\gamma_0 = \gamma \mu_0 > 0$ is the scaled gyromagnetic ratio, with $\gamma = e/2m$ (where e > 0 and m are the charge and mass of the electron, respectively), and $\alpha > 0$ is the dimensionless damping constant [10]. Table 1 lists all the physical variables used in this work, their units, and their numerical values.

2.1 Effective magnetic field H_{eff}

The effective magnetic field H_{eff} results from the sum of the exchange field H_{exch} and the anisotropy field H_{ani} :

$$oldsymbol{H}_{ ext{eff}} = oldsymbol{H}_{ ext{exch}} + oldsymbol{H}_{ ext{ani}}$$
 .

The exchange field is due to the Heisenberg exchange interaction and is written as

$$\boldsymbol{H}_{\text{exch}} = \frac{2A}{\mu_0 M_s} \Delta \boldsymbol{m},\tag{2}$$

with A > 0 the exchange constant and $\mu_0 > 0$ the vacuum permeability (see Table 1).

The anisotropy field is due to the existence of preferred directions in the magneto-crystalline structure of the material. Throughout the following, two cases of anisotropy field will be considered: uniaxial anisotropy (for cobalt systems) and cubic anisotropy (for nickel and iron systems), whose expressions are given below:

$$\boldsymbol{H}_{\text{ani, uniaxial}} = \frac{2K}{\mu_0 M_s} (\boldsymbol{e}_x \cdot \boldsymbol{m}) \boldsymbol{e}_x, \tag{3a}$$

$$\boldsymbol{H}_{\text{ani, cubic}} = -\frac{2K}{\mu_0 M_s} \sum_{(i,j,k) \in I} \left((\boldsymbol{e}_j \cdot \boldsymbol{m})^2 + (\boldsymbol{e}_k \cdot \boldsymbol{m})^2 + (\boldsymbol{e}_j \cdot \boldsymbol{m})^2 (\boldsymbol{e}_k \cdot \boldsymbol{m})^2 \right) (\boldsymbol{e}_i \cdot \boldsymbol{m}) \boldsymbol{e}_i, \tag{3b}$$

where $I = \{(x, y, z), (y, z, x), (z, x, y)\}$ and K > 0 is the anisotropy constant (assumed identical in all three directions of space for the cubic case), see Table 1.

In the following, we will assume that the ferromagnetic domain is not subjected to any external magnetic field, so that no Zeeman energy is present. The demagnetizing field (due to the magnetic field generated by the nanowire or nanolayer itself) and the dipolar interactions are also not taken into account.

Universal constants							
γ	gyromagnetic rati	0	$1.76 \times 10^{11} \text{ rad s}^{-1} \text{T}^{-1}$				
μ_0	vacuum permeabi	lity	$4\pi \times 10^{-7} \text{ NA}^{-2}$				
γ_0	rescaled gyromagi	netic ratio	$\gamma \mu_0 \ \mathrm{mA^{-1}s^{-1}}$				
k_B	Boltzmann consta	int	$1.38 \times 10^{-23} \text{ JK}^{-1}$				
Magnetic bulk parameters Cobalt Iron Nickel				Nickel			
A	exchange constant	$3 \times 10^{-11} \text{ Jm}^{-1}$	$2.1 \times 10^{-11} \text{ Jm}^{-1}$	$9 \times 10^{-12} \text{ Jm}^{-1}$			
K	anisotropy constant	$5.2 \times 10^5 \mathrm{~Jm^{-3}}$	$4.8 \times 10^4 \mathrm{~Jm^{-3}}$	$-5.7 \times 10^3 \text{ J.m}^{-3}$			
M_s	saturation magnetization	$1.4 \times 10^6 \mathrm{Am^{-1}}$	$1.7 \times 10^6 \mathrm{~Am^{-1}}$	$4.9 \times 10^5 \mathrm{~Am^{-1}}$			
$a_{\rm eff}$	lattice constant	0.25 nm	$0.286~\mathrm{nm}$	$0.345~\mathrm{nm}$			
$m{H}_{ m ani}$	anisotropy field	uniaxial	cubic	cubic			
$T_{\rm C}$	Curie temperature	1388 K	1043 K	$627~\mathrm{K}$			
α	Damping parameter	0.5	0.5	0.5			

Table 1: Top: Values of the universal constants used in this work. Bottom: Magnetic parameters for bulk cobalt, iron, and nickel. Sources: [17, 6, 23].

2.2 Thermal fluctuations

The deterministic LLG equation considered above is valid in the zero-temperature regime. However, thermal effects obviously influence the magnetic properties, first and foremost by cancelling out the spontaneous magnetization of a ferromagnetic material above a certain critical temperature (Curie temperature $T_{\rm C}$). The material then goes from a ferromagnetic to a paramagnetic state when $T_{\rm C}$ is crossed.

In order to model thermal fluctuations, an additional random field is added to the effective magnetic field, following the idea of W.F. Brown [3], so that we have:

$$\boldsymbol{H}_{\mathrm{eff}} = \boldsymbol{H}_{\mathrm{exch}} + \boldsymbol{H}_{\mathrm{ani}} + \boldsymbol{H}_{\mathrm{stocha}} \; .$$

The random thermal field $\boldsymbol{H}_{\text{stocha}}$ is an isotropic Gaussian white-noise vector process of variance $\nu^2 \in \mathbb{R}$. More precisely, $\boldsymbol{H}_{\text{stocha}}$ may be written as: $\boldsymbol{H}_{\text{stocha}}(t)dt = \nu d\boldsymbol{W}(t)$, where $\boldsymbol{W}(t) = (W_1(t), W_2(t), W_3(t))^{\text{T}}$ is a classical time-continuous Wiener process.

Wiener process. The main properties of the stochastic field W(t) (and so $H_{\text{stocha}}(t)$) are listed below, denoting $\langle \cdot \rangle = \mathbb{E}(\cdot)$ the statistical average [19, 5, 26]:

- Space homogeneity: \boldsymbol{W} only depends on t and not on \boldsymbol{x} ,
- Continuous time random process: $W(t), \forall t \ge 0$,
- Null mean: $\langle \boldsymbol{W}(t) \rangle = 0, \forall t \ge 0,$
- Decorrelated spatial components and vanishingly small autocorrelation time: $\langle W_i(t)W_j(t')\rangle = \delta_{ij}\delta(t-t'), \forall i, j \in \{1, 2, 3\}$ (the indices of spatial components) and $t, t' \in \mathbb{R}^+$. Here, $\delta(\cdot)$ is the Dirac distribution and δ_{ij} is the Kronecker symbol.

Variance. The standard deviation ν (and thus the variance ν^2) is directly related to the temperature T thanks to the following relation, obtained by the fluctuation-dissipation theorem [3, 26] adapted here to the expression of Eq. (1):

$$\nu^2 = \frac{2\alpha k_B T}{\gamma_0 \mu_0 M_s V},\tag{4}$$

where k_B is the Boltzmann constant (see Table 1) and V stands for a characteristic volume that depends on the internal crystalline structure of the material (which can be a Face-Centered Cubic lattice (FCC) as in the case of nickel, a Body Centered Cubic lattice (BCC) as in iron, or a Hexagonal Close-Packed lattice (HCP) for cobalt). Following the notation of [12], the shorter lattice distance is called the lattice constant a_{eff} and the corresponding characteristic volume is $V = a_{\text{eff}}^3$.

Stochastic Landau-Lifshitz-Gilbert equation. Consequently, the Landau-Lifshitz-Gilbert equation (1) is modified to take the form of a stochastic partial differential equation (SPDE)

$$d\boldsymbol{m} = -\gamma_0 \boldsymbol{m} \times (\boldsymbol{H}_{\text{eff}} dt + \nu d\boldsymbol{W}) - \gamma_0 \alpha \boldsymbol{m} \times [\boldsymbol{m} \times (\boldsymbol{H}_{\text{eff}} dt + \nu d\boldsymbol{W})].$$
(5)

All physical constants used in the forthcoming simulations are summarized in Table 1.

In order to preserve the constraint that the magnetic moment \boldsymbol{m} be on the unit sphere, i.e. $\|\boldsymbol{m}(t,\boldsymbol{x})\| = 1, \ \forall \boldsymbol{x} \in \mathbb{R}^3 \text{ and } t \geq 0$, we interpret the above stochastic LLG equation in the Stratonovich sense; see [20] for the issues posed by using Itô's approach.

2.3 Temperature scaling with the computational cell size

The variance of the stochastic magnetic field used to model thermal effects depends not only on the temperature T, but also on the characteristic volume V, see Eq. (4). In principle, this volume is related to the lattice constant, i.e. $V = a_{\text{eff}}^3$, but in practice a_{eff} is much smaller than the spatial step Δx used in the simulations. However, if one takes instead $V = \Delta x^3$, the simulation results will depend on the computational cell size, which is not an acceptable situation. At a fundamental level, this is due to the fact that the effective exchange constant varies with the size of the coarse-graining block [11].

In order to suppress this unwanted numerical effect, we follow the procedure recently suggested by Hahn [12], which relies on a scaling of the temperature with the spatial step Δx . The argument goes as follows: near the Curie temperature, the ferromagnetic behaviour disappears because the energy density of the thermal fluctuations $k_B T/V$, which favor random orientations of the spin, becomes similar to the energy density of the exchange interactions $A|\nabla \boldsymbol{m}|^2$, which favor magnetic order. Hence, we write:

$$\frac{k_B T}{a^3} \sim \frac{A|\boldsymbol{m}|^2}{a^2},\tag{6}$$

where a is a characteristic length that can be either the lattice constant a_{eff} or the computational cell size Δx . From Eq. (6) it is clear that, in order for the magnetic moment to be independent on the averaging volume a^3 , the temperature must scale as $T \sim a$.

Therefore, we define a "numerical" temperature as

$$T_{\rm num} = \frac{\Delta x}{a_{\rm eff}} T_{\rm eff}$$

According to the above considerations, taking a volume $V = \Delta x^3$ together with the temperature T_{num} should give results that are independent on Δx and identical to those obtained using the "physical" volume $V = a_{\text{eff}}^3$ and the real temperature T. This approach was recently tested by Hahn [12], who indeed observed near independence of T_{C} on the cell size up to $\Delta x = 4$ nm for ferromagnetic thin films. Following this procedure, the numerical variance of the fluctuating field is defined as

$$\nu_{\rm num}^2 = \frac{2\alpha k_B \frac{\Delta x}{a_{\rm eff}} T}{\gamma_0 \mu_0 M_s \Delta x^3},\tag{7}$$

which replaces Eq. (4) in the simulations. This expression may also be interpreted as meaning that the numerical characteristic volume to be taken into account is $V = a_{\text{eff}} \Delta x^2$.

3 Computational method

The stochastic LLG equation (5) is solved numerically using a Python code.¹ The simulations are performed on the time interval $[0, t_f]$, with t_f the final time, and on a 3D finite domain $[0, L_x] \times [0, L_y] \times [0, L_z]$. To mimic a 1D nanowire, this numerical domain is taken with a small square cross-section in the (e_y, e_z) plane: $[0, L_x] \times [0, d] \times [0, d]$, with $d \ll L_x$. To mimic a 2D nanolayer, the 3D domain is taken with a small thickness in the e_z direction: $[0, L_x] \times [0, L_y] \times [0, d]$, with $d \ll L_x$. Figure 1 illustrates those two geometries. All numerical parameters are listed in Table 2.



Figure 1: Illustration of the two generic geometries coresponding to a 1D nanowire (left) and a 2D nanolayer (right)

Discretization. Numerically, let $\Delta t > 0$ and $\Delta x = \Delta y = \Delta z > 0$ be the time step and the space steps in each space direction, respectively. We define time-discrete and space-discrete points with $N = \lfloor \frac{t_f}{\Delta t} \rfloor$, $J_x = \lfloor \frac{L_x}{\Delta x} \rfloor$, $J_y = \lfloor \frac{L_y}{\Delta x} \rfloor$, $J_z = \lfloor \frac{L_z}{\Delta x} \rfloor$

$$t^n = n\Delta t, \qquad 0 \le n \le N$$

and

$$(x_i, y_j, z_k) = (i\Delta x, j\Delta x, k\Delta x), \quad 0 \le i \le J_x, \quad 0 \le j \le J_y, \quad 0 \le k \le J_z.$$

The numerical solution $m_{i,j,k}^n$ approximates the exact one $m(t^n, x_i, y_j, z_k)$ on each discrete point.

As the LLG equation (1) is valid at mesoscopic – and not atomistic – length scales, the spatial steps Δx , Δy , Δz are each much larger than the lattice constant a_{eff} , and the continuous magnetic moment vector filed $\boldsymbol{m}(t, \boldsymbol{x})$ actually represents an average of the atomic spins over a volume $\Delta x \Delta y \Delta z$.

¹Available at: https://gitlab.math.unistra.fr/llg3d/llg3d

Discretization time and space parameters					
Δt	time step	10 fs			
t_f	final time of the simulation	50 ps			
N	number of time iterations	5000			
n	time index	$0 \le n \le N$			
$\Delta x = \Delta y$	$=\Delta z$ space size of the meshes	1.0 nm			
d	small size parameter	11.0 nm $\leq d \leq$ 41.0 nm			
L_x, L_y, L_z	size of the ferromagnetic ob-	nanowire ($L_x = 6000 \text{ nm}, L_y = L_z = d \text{ nm}$)			
	ject	nanolayer $(L_x = L_y = 600 \text{ nm}, L_z = d \text{ nm})$			
J_x, J_y, J_z	number of mesh points	nanowire $(J_x = 6000, J_y = J_z = \lfloor d \rfloor)$ nanolayer $(J_x = J_y = 600, J_z = \lfloor d \rfloor)$			
i, j, k	space indices	$0 < i < J_x, 0 < j < J_y, 0 < k < J_z$			
	Numerica	l variables			
m^0	initialization of the magnetic mo- ments	$\begin{pmatrix} 1\\0\\0 \end{pmatrix} \text{ for all points } (x_i, y_j, z_k)$			
$\overline{m}_1(t)$	spatial average of one realization	$\frac{1}{L_x L_y L_z} \int_{[0,L_x] \times [0,L_y] \times [0,L_z]} m_1(t,\boldsymbol{x}) d\boldsymbol{x}$			
au	transient time behavior of $\overline{m}_1(t)$	40 ps			
$M_{\rm tot}$	total magnetization (spatial and stochastic averages at t_f)	$\frac{1}{t_f - \tau} \int_{\tau}^{t_f} \frac{1}{L_x L_y L_z} \int_{[0, L_x] \times [0, L_y] \times [0, L_z]} m_1(t, \boldsymbol{x}) d\boldsymbol{x} dt$			
$t_{\rm conv}$	convergence time for $\overline{m}_1(t)$ to reach its plateau state $M_{\rm tot}$	$\inf_{t\in[0,t_f]} \overline{m}_1(t) - M_{\text{tot}} < 0.1$			

Table 2: Numerical parameters used in the Python code

Time evolution: Heun method. For consistency with the continuous problem, the stochastic LLG equation (5) must be discretized using a numerical method whose solution converges to the Stratonovich continuous solution. For this purpose, the modified Heun method [27] is chosen for the time integration and a second-order finite difference method is used for the discretization of the Laplacian operator.

Following [18], for further simplicity, we rewrite Eq. (5) as

$$d\boldsymbol{m} = \boldsymbol{F}(\boldsymbol{m}, t)dt + \sum_{j \in \{1, 2, 3\}} \boldsymbol{G}_j(\boldsymbol{m}) \,\nu \, dW_j(t), \tag{8}$$

with

$$\boldsymbol{F}(\boldsymbol{m},t) = -\gamma_0 \boldsymbol{m} \times \boldsymbol{H}_{\text{eff}} - \gamma_0 \alpha \, \boldsymbol{m} \times (\boldsymbol{m} \times \boldsymbol{H}_{\text{eff}})$$

being the deterministic part and $G_j = \begin{pmatrix} G_{1,j} \\ G_{2,j} \\ G_{3,j} \end{pmatrix}$ the factor term of the stochastic process, with

$$G_{i,j} = \gamma_0 m_k \epsilon_{i,j,k} - \gamma_0 \alpha (m_i m_j - \delta_{ij}),$$

where $\epsilon_{i,j,k}$ is the Levi-Civita symbol.

After initializing the magnetization at the initial time t = 0: $\boldsymbol{m}_{i,j,k}^0 = \begin{pmatrix} m_1 \\ m_2 \\ m_3 \end{pmatrix}_{i,j,k}^0 = \boldsymbol{m}(0, x_i, y_j, z_k),$

the (stochastic) Heun method consists in the following steps to go from the time step n to the time step n + 1:

- Generate a random vector $\mathbf{R}^n \in \mathbb{R}^3$ according to a reduced centered normal distribution, using a pseudo-random number generator. Define $\Delta \mathbf{W}^n = \sqrt{\Delta t} \mathbf{R}^n$;
- Compute ν_{num} , the numerical version of the standard deviation ν (more details are given below);
- Define $\kappa_1 = F(\boldsymbol{m}^n, t^n)$ and $\boldsymbol{s}_{1,j} = \boldsymbol{G}_j(\boldsymbol{m}^n)$;
- Define $\boldsymbol{\kappa}_2 = \boldsymbol{F}(\boldsymbol{m}^n + \Delta t \boldsymbol{\kappa}_1 + \sum_{j \in \{1,2,3\}} \boldsymbol{s}_{1,j} \nu_{\text{num}} \Delta W_j^n, t^n + \Delta t)$ and $\boldsymbol{s}_{2,j} = \boldsymbol{G}_j(\boldsymbol{m}^n + \Delta t \boldsymbol{\kappa}_1 + \sum_{j \in \{1,2,3\}} \boldsymbol{s}_{1,j} \nu_{\text{num}} \Delta W_j^n);$
- Update $\boldsymbol{m}^{n+1} = \boldsymbol{m}^n + \left(\frac{1}{2}\boldsymbol{\kappa}_1 + \frac{1}{2}\boldsymbol{\kappa}_2\right)\Delta t + \sum_{j\in\{1,2,3\}} \left(\frac{1}{2}\boldsymbol{s}_{1,j} + \frac{1}{2}\boldsymbol{s}_{2,j}\right)\nu_{\text{num}}\Delta W_j^n;$
- Renormalize the magnetic moment: $m^{n+1} = \frac{m^{n+1}}{\|m^{n+1}\|}$, so that it remains on the unit sphere \mathbb{S}^2 .

A mid-point numerical technique would be also possible alternative to the Heun method, see [5, 26].

The choice of a time-explicit discretization of the Laplacian operator induces a restrictive condition on the time step Δt and the space step Δx to ensure the stability of the scheme: $\Delta t \leq \Delta x^2/2$ (Courant-Friedrichs-Lewy condition).

At the domain boundaries, we take the usual Neumann condition: $\partial \boldsymbol{m}/\partial \boldsymbol{n} = 0$, where \boldsymbol{n} is the outgoing normal vector.

4 Numerical code validation

In the forthcoming simulations, three types of ferromagnetic materials will be considered: (i) nickel with a FCC lattice and cubic anisotropy, (ii) iron with a BCC lattice and a cubic anisotropy, and (iii) cobalt with a HCP lattice and uniaxial anisotropy. For each case, we shall study both 1D nanowires and 2D nanolayers. All physical parameters are listed in Table 1.

Here, we will perform several tests to validate our numerical code. In the following sections, we will focus on the scaling of the Curie temperature with the size of the system, for each type of nanoobject. We recall that our code relies on the time-dependent LLG equation. We solve numerically this equation with a fully magnetized initial condition, where $\mathbf{m}(t=0)$ is uniform and directed along the \mathbf{e}_x axis, and a given temperature. Then, we wait that magnetic moment relaxes to a lower value under the effect of the temperature and determine its value by averaging over a sufficiently long period of time.

4.1 Test-case details

Except for the following Sec. 4.2 – where the independence of the results on the space and time discretizations are tested on a 3D cube – all numerical simulations are preformed on three ferromagnetic materials (cobalt, iron and nickel) and two geometries (see Figure 1):

- 1D nanowire with small square cross-section in the (e_y, e_z) plane: $[0, L_x] \times [0, d] \times [0, d]$ with $L_x = 6000$ nm and 11 nm $\leq d \leq 41$ nm;
- 2D nanolayer with small thickness in the e_z axis: $[0, L_x] \times [0, L_y] \times [0, d]$ with $L_x = L_y = 600$ nm and 11 nm $\leq d \leq 41$ nm.

The numerical parameters are always fixed to (see Table 2):

$$\Delta t = 10 \text{ fs}, \quad t_f = 50 \text{ ps}, \quad N = 5000, \quad \Delta x = \Delta y = \Delta z = 1 \text{ nm}.$$

The initialization of the magnetic moments m^0 is chosen uniform and directed along the e_x axis in

all test cases: $\boldsymbol{m}_{i,j,k}^0 = \begin{pmatrix} 1\\ 0\\ 0 \end{pmatrix}$ for all i, j, k.

With the choice of initialization, the magnetization is initially equal to 1 (when the magnetic moments are all aligned and have a norm equal to 1), then falls to zero at the Curie temperature (when the magnetic moments are randomly aligned due to the thermal noise). Since Eq. (5) is stochastic, the average of the magnetic moments m over the entire ferromagnetic domain may differ from one realization to another, so this average should be calculated over several realizations. Since the initialization is oriented along the e_x axis and in the absence of any external magnetic field, the average of m along this direction, i.e. m_1 , is enough to characterize the magnetic state of the system. Hence, we define the total (in space) magnetization

$$M_{\text{tot}} = \left\langle \frac{1}{L_x L_y L_z} \int_{[0, L_x] \times [0, L_y] \times [0, L_z]} m_1(t_f, \boldsymbol{x}) d\boldsymbol{x} \right\rangle,$$
(9)

with $\langle \cdot \rangle$ denoting the statistical average over many realizations. In order to simplify this calculation, we assume that the stochastic process of Eq. (5) is ergodic, so that the statistical average may be replaced by the time average for a single, sufficiently long realization. In practice, we plot several realizations, look at the time τ after which the transient regime gives way to the stationary regime, and finally take the time average from this *transient time* τ up to the final time t_f . Thus, the total magnetization is now defined as

$$M_{\text{tot}} = \frac{1}{t_f - \tau} \int_{\tau}^{t_f} \frac{1}{L_x L_y L_z} \int_{[0, L_x] \times [0, L_y] \times [0, L_z]} m_1(t, \boldsymbol{x}) d\boldsymbol{x} dt = \frac{1}{t_f - \tau} \int_{\tau}^{t_f} \overline{m}_1(t) dt.$$
(10)

Figure 2 illustrates the spatial average of the x component of the magnetic moment $\overline{m}_1(t) = \frac{1}{L_x L_y L_z} \int_{[0,L_x] \times [0,L_y] \times [0,L_z]} m_1(t, \mathbf{x}) d\mathbf{x}$ for one statistical realization, for cobalt (top), iron (middle) and nickel (bottom). Two geometries of nanowire are tested: $[0, 1680] \times [0, 11] \times [0, 11]$ with $\Delta x = 1$ nm (left column) and $[0, 120] \times [0, 41] \times [0, 41]$ with $\Delta x = 1$ nm (right column). Other numerical parameters Δt , t_f and N are defined in Table 2. Different temperatures are used (represented with different colors) and lead to the same conclusion for all test cases: $\tau = 0.8 t_f = 40$ ps is a correct choice both for reaching the stationary state and for having enough time left for a representative average (this choice represents a time average over the last 1000 time steps, and $t_f - \tau = 10$ ps in Eq. (10)).

In practice, the Curie temperature is determined numerically by plotting M_{tot} as a function of the temperature T, and defining T_{C} as the temperature for which M_{tot} is smaller than a certain threshold, fixed to 0.1: $T_{\text{C}} := \underset{T}{\operatorname{argmin}} M_{\text{tot}}(T) < 0.1.$

4.2 Dependence on the numerical parameters

Here, we show that our results do not depend on either the time step Δt or the computational cell size Δx .

Figure 3 shows the total magnetization M_{tot} as a function of the temperature for different cell sizes, going from 1 nm to 5 nm, for a cubic object of dimensions 50 nm × 50 nm × 50 nm, for cobalt, iron and nickel. All other parameters are identical ($\Delta t = 10$ fs, $t_f = 50$ ps, N = 5000 and $\tau = 40.0$ ps). The results are indeed independent on Δx , and the computed Curie temperatures are very close to the experimental values for the bulk materials (see Table 1). A slight discrepancy starts occurring for iron at $\Delta x = 5$ nm.

Figure 4 shows the dependence of the numerical results with respect to the time step Δt , again for cubic nano-objects of side 50 nm, with computational cell size $\Delta x = 1$ nm. The final time is always $t_f = 50$ ps, so that the number of time steps is $N = 5 \times 10^3$ for $\Delta t = 10$ fs (blue curve), $N = 10^4$ for $\Delta t = 5$ fs (red curve), and $N = 2 \times 10^4$ for $\Delta t = 2.5$ fs (green curve). According to the value of Δt , the time-averaged M_{tot} in Eq. (10) includes the last 1000, 2000 or 4000 time iterations. The computed Curie temperature varies only slightly with the time step, and appears to have converged for $\Delta t = 5$ fs.



Figure 2: Spatially averaged x component of the magnetic moment $\overline{m}_1(t)$ for one statistical realization, as a function of time t for a ferromagnetic nanowire. Colors correspond to different temperatures, as indicated on the figure. Top panels: cobalt; middle panels: iron; bottom panels: nickel. The left column corresponds to nanowires with dimensions (in nm): $1680 \times 11 \times 11$, the right column to nanowires with dimensions (in nm): $120 \times 41 \times 41$.



Figure 3: Total magnetization M_{tot} , from Eq. (10), as a function of the temperature, for cubic cobalt (left panel), iron (right panel) and nickel (middle panel) nano-objects with dimensions 50 nm × 50 nm × 50 nm. The different symbols and colors stand for different computational cell sizes Δx , going from 1 nm to 5 nm. The black vertical dash-dotted lines represent the bulk Curie temperatures as given in Table 1.

4.3 Magnetization curve: Bloch's law and Curie's law

In this section, we check that the numerically calculated magnetization $M_{\text{tot}}(T)$ satisfies the standard Bloch's and Curie's laws, respectively at low temperatures $T \ll T_{\text{C}}$ and near the Curie temperature, $T \lesssim T_{\text{C}}$. As we have already verified that the spatial and temporal steps do not influence the result, Δt and Δx will be fixed as specified in Table 2, i.e. $\Delta t = 10$ fs and $\Delta x = 1$ nm.

Figure 5 illustrates the behavior of the magnetization curve $M_{tot}(T)$ for the two geometric configurations considered here (nanowires and nanolayers), for iron (red triangles), cobalt (blue circles) and nickel (green crosses). Results are in broad agreement with the expected magnetization curves, and the computed Curie temperatures are close to the experimental values found in the literature for bulk materials [17], see Table 1.



Figure 4: Total magnetization M_{tot} , from Eq. (10), as a function of temperature, for a cobalt (left), iron (right) or nickel (middle) nanowire with dimensions 50 nm×50 nm×50 nm. The different symbols stand for different time steps $\Delta t = 2.5$ fs (green crosses), 5 fs (red circles), and 10 fs (blue crosses). The computational grid size is $\Delta x = 1$ nm. The black vertical dash-dotted lines represent the bulk Curie temperatures as given in Table 1.

Bloch's law states that total magnetization $M_{tot}(T)$, for low temperatures, behaves as follows:

$$M_{\rm tot}(T) \underset{T \to 0}{\sim} 1 - \left(\frac{T}{T_{\rm C}}\right)^{3/2}$$

which can be rewritten as: $\log(1 - M_{\text{tot}}) \sim \frac{3}{2} \log (T/T_{\text{C}})$. Figure 6 checks this behaviour on a log-log scale, for a nanowire (left) and a nanolayer (right), with sizes corresponding to the two extreme cases in Table 3, i.e. d = 11nm and 41 nm. The theoretical 3/2 slope is represented as a solid black line and matches the numerical results quite well.

Next, we check the Curie law, valid near $T_{\rm C}$:

$$M_{\rm tot}(T) \underset{T \to T_{\rm C}}{\sim} \left(1 - \frac{T}{T_{\rm C}}\right)^{1/2},$$

which may be rewritten as: $\log(M_{\text{tot}}) \sim \frac{1}{2} \log \left(1 - \frac{T}{T_{\text{C}}}\right)$. Figure 7 shows the behavior of the magne-



Figure 5: Total magnetization M_{tot} (10) with respect to temperature with numerical parameters detailed in Table 2. The Curie temperature corresponds to the first temperature at which magnetization falls to zero. Simulation results are represented by dots, the solid curves are an interpolation based on cubic splines.



Figure 6: Bloch's law. Behavior of $1 - M_{tot}(T)$ as a function of $T/T_{\rm C}$ in logarithmic scale. The materials are represented by different colors: iron (red), cobalt (blue) and nickel (green). The left panel corresponds to nanowires and the right panel to nanolayers, with sizes d = 11 nm (crosses) and d = 41 nm (dots). Each curve was multiplied by a multiplicative factor for easier reading. The black solid lines represent the theoretical 3/2 slope.

tization M_{tot} as a function of $1 - T/T_{\text{C}}$ in logarithmic scale, for the same cases as those of Figure 6. Again, the numerical results match rather well the theoretical 1/2 slope.



Figure 7: Curie's law. Behavior of $M_{\text{tot}}(T)$ as a function of $1 - T/T_{\text{C}}$ in logarithmic scale. The materials are represented by different colors: iron (red), cobalt (blue) and nickel (green). The left panel corresponds to nanowires and the right panel to nanolayers, with sizes d = 11 nm (crosses) and d = 41 nm (dots). Each curve was multiplied by a multiplicative factor for easier reading. The black solid lines represent the theoretical 1/2 slope.

5 Finite-size effects on the Curie temperature

This section is devoted to the study of the influence of size effect on the magnetization curve and Curie temperature for nanometric objects, both in 1D (nanowires) and 2D (nanolayers). The objective is to vary the cross-section of the nanowire or the thickness of the nanolayer and study the variations induced in the Curie temperature. Throughout this section, numerical parameters are chosen as listed in Table 2.

5.1 Size effects on the magnetization curve

For all tested geometries, the computed Curie temperatures are close enough to the experimental values reported in the literature. This is achieved thanks to the scaling of the fluctuating thermal field as detailed in Sec. 2.3. Nevertheless, we observe small variations with the size parameter d, which corresponds to the side of the square cross-section of a nanowire or the thickness of a nanolayer. Figure 8 (for nanowires) and Figure 9 (for nanolayers) show the magnetization curves $M_{\text{tot}}(T)$, and illustrate how the Curie temperature increases with increasing size d. The computed values of T_{C} are summarized in Table 3. We also observe greater variability in $M_{\text{tot}}(T)$ for nanowires than for nanolayers. Size effects then appear to be stronger for lower-dimensional structures.

5.2 Power-law scaling of the Curie temperature

Theoretical considerations [9] indicate that the Curie temperature should vary with the size d following a power-law of the type:

$$\frac{T_{\rm C}(\infty) - T_{\rm C}(d)}{T_{\rm C}(\infty)} = \left(\frac{\xi_0}{d}\right)^{\lambda},\tag{11}$$



Figure 8: Total magnetization $M_{\text{tot}}(T)$ as a function of the temperature for nanowires of different materials, with cross-section sizes going from d = 11 nm to d = 41 nm. Top panels: cobalt; middle panels: iron; bottom panels: nickel. The right column is a zoom near the Curie temperature.

where λ is the critical exponent, ξ_0 is the correlation length at zero temperature, $T_{\rm C}(\infty)$ is the Curie temperature of the bulk, and $T_{\rm C}(d)$ the Curie temperature of a finite nano-object of size d. This type of power-law has been observed in many experiments [28, 14, 21, 29, 33, 31] and numerical simulations [1, 25]. Experimental works yielded correlation length ξ_0 of the order of a few



Figure 9: Total magnetization $M_{\text{tot}}(T)$ as a function of the temperature for nanolayers of different materials, with thiknesses going from d = 11 nm to d = 41 nm. Top panels: cobalt; middle panels: iron; bottom panels: nickel. The right column is a zoom near the Curie temperature.

nanometers, with critical exponents in the range $\lambda \in [1 - 1.6]$. In contrast, an atomistic mean-field model [25] yielded larger values, close to $\lambda = 2$ (range: $\lambda \in [1.82 - 2.17]$), for magnetite nanoparticles of different shapes and sizes. These values are also to be compared to those obtained from the 3D Heisenberg model ($\lambda = 1.4$) and the 3D Ising model ($\lambda = 1.58$).

Nanowire $L_x \times d \times d$ with $L_x = 6000$ nm			Nanola	Nanolayer $L_x \times L_y \times d$ with $L_x = L_y = 600$ nm			
$d \; [nm]$	Cobalt	Iron	Nickel	d [nm]	Cobalt	Iron	Nickel
41	1427.26	1090.05	579.62	41	1433.91	1095.33	582.39
36	1423.74	1087.57	578.13	36	1432.20	1093.41	581.67
31	1421.56	1085.81	577.23	31	1430.68	1092.13	581.01
26	1414.62	1082.05	573.87	26	1428.68	1091.49	579.81
21	1406.83	1076.85	571.05	21	1422.79	1087.65	578.07
20	1401.23	1072.13	569.31	20	1421.75	1087.25	577.71
19	1397.04	1073.01	568.05	19	1421.27	1087.49	577.41
18	1395.52	1069.65	566.91	18	1419.85	1085.01	576.33
17	1391.72	1069.17	564.45	17	1416.14	1083.41	575.61
16	1385.55	1062.61	561.69	16	1415.10	1082.05	574.71
15	1382.13	1062.45	560.67	15	1413.20	1080.53	573.63
14	1375.19	1053.65	558.15	14	1410.35	1080.13	572.73
13	1360.18	1045.89	552.69	13	1406.55	1076.37	570.87
12	1352.11	1043.65	549.33	12	1400.37	1072.21	568.95
11	1342.04	1036.53	544.83	11	1398.09	1071.33	567.33

Table 3: Curie temperatures (in Kelvin) obtained from the numerical simulations, for nanowires (left) and nanolayers (right) of different sizes and different materials.

In the analysis of our simulation results, the Curie temperature of the bulk $T_{\rm C}(\infty)$ is in fact replaced by the Curie temperature of the largest structure that we consider $T_{\rm C}(d_{\rm max})$, that is $d_{\rm max} =$ 41 nm, see Table 3. Figure 10 (for nanowires) and Figure 11 (for nanolayers) illustrate this powerlaw behaviour for the three materials considered here, both on a linear scale (left panels) and on a logarithmic scale (right panels). Blue circles correspond to the numerical results $T_{\rm C}(d)$ extracted from Table 3. The red solid lines correspond to the theoretical power-law (11). The exponent λ is deduced by fitting a log-log straight line through the numerical points using a least-square method, and then ξ_0 is obtained by finding the intercept $\lambda \log \xi_0$ of this line with the vertical axis. The last two or three points further to the right deviate from the power-law, and were therefore discarded in the fitting procedure.

The computed values of the correlation length ξ_0 and the critical exponent λ are reported on each figure. For nanowires, ξ_0 ranges from 2.77 nm to 3.02 nm, while for nanolayers it varies from 1.55 nm to 1.82 nm. In both cases, the smallest value is found to be for iron, whereas the largest values is for nickel. These values are broadly in good agreement with those observed in the experiments.

As to the critical exponent, we obtain $\lambda = 2.12 - 2.14$ (a range that is probably within the numerical uncertainty) for all three materials in the case of nanowires. For nanolayers, we obtain $\lambda = 1.90, 1.92$ and 2.00, for cobalt, iron and nickel, respectively. It is remarkable that all exponents are close to $\lambda = 2$, which is also the value observed in atomistic mean-field simulations [25].

5.3 Nonequilibrium properties

Although we have used our code to study steady-state phenomena, such as the dependence of the magnetization curve and Curie temperature with size, our approach is fundamentally time-



Figure 10: Behavior of the Curie temperature as a function of the cross-section size d, for nanowires of different materials: cobalt (top panels), iron (middle panels) and nickel (bottom panels). Numerical results are shown as blue dots, while the solid blue and red lines represent the theoretical power-law of Eq. (11). The left column shows results on a linear scale, while the right column on a log-log scale. The correlation length ξ_0 and critical exponent λ can be read on each figure of the right column as: $(\xi_0/d)^{\lambda}$.



Figure 11: Behavior of the Curie temperature as a function of the thickness d, for nanolayers of different materials: cobalt (top panels), iron (middle panels) and nickel (bottom panels). Numerical results are shown as blue dots, while the solid blue and red lines represent the theoretical power-law of Eq. (11). The left column shows results on a linear scale, while the right column on a log-log scale. The correlation length ξ_0 and critical exponent λ can be read on each figure of the right column as: $(\xi_0/d)^{\lambda}$.



Figure 12: Evolution of the spatially-averaged x component of the magnetic moment $\overline{m}_1(t)$ for a nickel nanowire of cross-section d = 11 nm, for three different temperatures, T = 510 K, T = 587 K and T = 650 K. The corresponding convergence times ($t_{\text{conv}} = 1.9$ ps, 6.2 ps, and 11.2 ps) are shown on the figure. We also show the transient time $\tau = 40$ ps, which is the same for all simulations (time used to average the total magnetization M_{tot}).

dependent. Indeed, to obtain our results we solved numerically the time-dependent LLG equation (with thermal effects) and then deduced steady-state quantities through time and/or ensemble averages. However, the code could be used to investigate nonequilibrium properties, such as transient behaviors, the motion of domain walls, instabilities, etc. Over more commonly used statistical methods, this dynamical approach has the further advantage of being well-suited to study the fluctuations that appear in the vicinity of phase transitions. These fluctuations play a key role in finite systems, particularly when their dimensionality is low. This vast realm is left to future investigations. Here, we conclude our work by searching for a signature of the phase transition occurring at $T_{\rm C}$ in the dynamical behaviour of the magnetization. We do this by looking at the convergence time towards the equilibrium state.

In Figure 2, we observed that the convergence time to the plateau state depends on the temperature. More precisely, we define the *convergence time* as the first time at which the x component of the spatially-averaged magnetic moment $\overline{m}_1(t)$ becomes sufficiently close to the total magnetization M_{tot} (which corresponds to its plateau):

$$t_{\rm conv} = \inf_{t \in [0, t_f]} |\overline{m}_1(t) - M_{\rm tot}| < \varepsilon,$$
(12)

with the tolerance parameter ε fixed to 0.1. Figure 12 illustrates schematically this convergence time t_{conv} , and also shows the *transient time* τ , which is the time used to compute the average magnetization, see Eq. (10).

Figure 13 shows the convergence time, as a function of the temperature, for nanowires of size 6000 nm×d nm ×d nm and nanolayers of size 600 nm×600 nm ×d nm, for two values of d. First, we note that the convergence time t_{conv} is always smaller than the transient time τ taken to compute the average M_{tot} (t_{conv} has a maximum value around 20 ps, which is always smaller than $\tau = 40$ ps). This confirms that convergence to the plateau state takes place before τ and hence that the calculation of M_{tot} is correct.

This figure also shows that the convergence time peaks near the Curie temperature [22]. This is a dynamical signature that large fluctuations near $T_{\rm C}$ translate into longer times taken by the system to relax to its equilibrium state. The rapid increase of the relaxation time close to $T_{\rm C}$ is known as critical slowing down [24, 4], an effect which is characteristic of second-order phase transitions.

Moreover, Figure 13 illustrates the effect of size on this phase transition. The structures with the smallest size (d = 11 nm, blue curves) have longer convergence times t_{conv} and larger widths than the larger structures (d = 41 nm, orange curves). Also, the convergence times and the widths are larger for 1D nanowires than for 2D nanolayers. One can deduce that fluctuations near the transition temperature $T_{\rm C}$ are stronger for smaller and lower-dimensional structures.

6 Conclusion

In this work, we developed a computational code (written in Python) that solves the LLG equation of micromagnetism, including finite-temperature effects. By adopting an appropriate temperature scaling with the computational cell size Δx [12], it was possible to recover magnetization curves and Curie temperatures that match closely the experimental ones for cobalt, nickel and iron nanoobjects. Compared to fully atomistic simulations, our micromagnetic approach has the advantage of being less computationally expensive, as it relies on a mesoscopic description at a scale ℓ much larger than the lattice constant: $\ell \gg \Delta x \gg a_{\text{eff}}$. It is also more easily amenable to dynamical simulations to study, for instance, the motion of domain walls or other time-dependent phenomena.

Using this accurate computational tool, we investigated the size-dependence of the Curie temperature for 1D nanowires and 2D nanolayers, by varying the smallest size d of the system. We confirmed that the difference between the computed finite-size $T_{\rm C}$ and the bulk $T_{\rm C}$ follows a powerlaw of the type: $(\xi_0/d)^{\lambda}$, where ξ_0 is the correlation length at zero temperature and λ is a critical exponent. We obtained values of ξ_0 in the nanometer range, also in accordance with other simulations and experiments. The computed critical exponent was found to be close to $\lambda = 2$ for all considered materials and geometries, which is the expected result for a mean-field approach, but slightly larger than the values observed experimentally. Finally, the time-dependent model developed here represents an effective tool for studying thermal fluctuations near the ferromagnetic phase transition.

All in all, the behaviour of 1D and 2D ferromagnetic nano-objects, as a function of both temperature and size, was recovered with good precision and a relatively low computational cost in comparison to fully atomistic simulations. This computational tool may therefore be applied in the future to more complex configurations, involving for instance 3D structures and dynamical effects.

Acknowledgements

The authors gratefully acknowledge partial support by the ANR project MOSICOF ANR-21-CE40-0004. R. Côte acknowledges support from the University of Strasbourg Institute for Advanced Study (USIAS) for a Fellowship within the French national programme "Investment for the future" (IdEx-Unistra). The autors would like to thank Jérôme Lelong and Bertrand Dupé for a suggestion that helped improve the computer code, and Guillaume Ferriere, Ludovic Godard-Cadillac and Yannick Privat for the enriching discussions throughout the project. We also thank Riccardo Hertel for his



Figure 13: Convergence time t_{conv} , from Eq. (12), as a function of the temperature for cobalt (top panels), iron (middle panels) and nickel (bottom panels). Left column: nanowire geometry with 6000 nm×d nm; right column: nanolayer geometry with 600 nm×600 nm×d nm. Two values of d are considered: d = 11 nm (blue solid curve) and d = 41 nm (orange dash curve). The vertical lines correspond to the numerical Curie temperatures reported in Table 3, for d = 11 nm (blue vertical line) and d = 41 nm (orange vertical line).

thorough reading of the manuscript and many insightful comments.

References

- [1] E. Almahmoud, I. Kornev, and L. Bellaiche. Dependence of Curie temperature on the thickness of an ultrathin ferroelectric film. *Physical Review B*, 81:064105, 2010.
- [2] U. Atxitia, D. Hinzke, and U. Nowak. Fundamentals and applications of the Landau-Lifshitz-Bloch equation. Journal of Physics D: Applied Physics, 50(3):033003, 2016.
- [3] W. F. Brown. Thermal fluctuations of a single-domain particle. *Physical Review*, 130:1677, 1963.
- [4] O. Chubykalo-Fesenko, U. Nowak, R. W. Chantrell, and D. Garanin. Dynamic approach for micromagnetics close to the Curie temperature. *Physical Review B*, 74:094436, 2006.
- [5] M. d'Aquino, C. Serpico, G. Coppola, I. D. Mayergoyz, and G. Bertotti. Midpoint numerical technique for stochastic Landau-Lifshitz-Gilbert dynamics. *Journal of Applied Physics*, 99:08B905, 2006.
- [6] W. P. Davey. Precision Measurements of the Lattice Constants of Twelve Common Metals. *Physical Review*, 25:753–761, 1925.
- [7] M. Donahue and D. Porter. OOMMF User's Guide, Version 1.0, Interagency Report 6376. Technical report, National Institute of Standards and Technology, Gaithersburg, 1999.
- [8] R. F. L. Evans, D. Meilak, A. Naden, and A. Biternas. VAMPIRE, User Manual. Technical report, Department of Physics, The University of York, Heslington, York, 2018.
- [9] M. E. Fisher and M. N. Barber. Scaling Theory for Finite-Size Effects in the Critical Region. *Physical Review Letters*, 28:1516–1519, 1972.
- [10] T. Gilbert. A phenomenological theory of damping in ferromagnetic materials. *IEEE Transac*tions on Magnetics, 40(6):3443–3449, 2004.
- [11] G. Grinstein and R. Koch. Coarse Graining in Micromagnetics. Physical Review Letter, 90(20):207201, 2003.
- [12] M. B. Hahn. Temperature in micromagnetism : cell size and scaling effects of the stochastic Landau–Lifshitz equation. *Journal of Physics Communications*, 3:075009, 2019.
- [13] R. Hertel. tetmag. https://github.com/R-Hertel/tetmag, Aug. 2023.
- [14] F. Huang, G. J. Mankey, M. T. Kief, and R. F. Willis. Finite-size scaling behavior of ferromagnetic thin films. *Journal of Applied Physics*, 73(10):6760–6762, 1993.
- [15] M. Kirschner, T. Schrefl, F. Dorfbauer, G. Hrkac, D. Suess, and J. Fidler. Cell size corrections for nonzero-temperature micromagnetics. *Journal of Applied Physics*, 97:10E301, 2005.
- [16] M. Kirschner, T. Schrefl, G. Hrkac, F. Dorfbauer, D. Suess, and J. Fidler. Relaxation times and cell size in nonzero-temperature micromagnetics. *Physica B: Condensed Matter*, 372(1):277– 281, 2006. Proceedings of the Fifth International Symposium on Hysteresis and Micromagnetic Modeling.

- [17] C. Kittel and P. McEuen. Introduction to solid state physics. John Wiley & Sons, 2018.
- [18] G. Klughertz. Ultrafast magnetization dynamics in magnetic nanoparticles. PhD thesis, University of Strasbourg, 2016.
- [19] G. Klughertz, P. A. Hervieux, and G. Manfredi. Autoresonant control of the magnetization switching in single-domain nanoparticules. *Journal of Physics D: Applied Physics*, 47:345004, 2014.
- [20] S. Labbé and J. Lelong. Stochastic modelling of thermal effects on a ferromagnetic nano particle. Journal of Dynamics and Differential Equations, 32:1273–1290, 2020.
- [21] Y. Li and K. Baberschke. Dimensional crossover in ultrathin Ni(111) films on W(110). Physical Review Letters, 68:1208–1211, 1992.
- [22] E. Maurat and P.-A. Hervieux. Thermal properties of open-shell metal clusters. New Journal of Physics, 11(10):103031, 2009.
- [23] F. Ono and H. Maeta. Determination of lattice parameters in Hcp cobalt by using X-Ray bond's method. Le Journal de Physique Colloques, 49(C8):C8-63, 1988.
- [24] P. Peczak and D. P. Landau. Dynamical critical behavior of the three-dimensional Heisenberg model. *Physical Review B*, 47:14260–14266, 1993.
- [25] C. Penny, A. R. Muxworthy, and K. Fabian. Mean-field modelling of magnetic nanoparticles: The effect of particle size and shape on the Curie temperature. *Physical Review B*, 99:174414, 2019.
- [26] C. Ragusa, M. d'Aquino, C. Serpico, B. Xie, M. Repetto, G. Bertotti, and D. Ansalone. Full micromagnetic numerical simulations of thermal fluctuations. *IEE Transactions on magnetics*, 45:10, 2009.
- [27] W. Rüemelin. Numerical Treatment of Stochastic Differential Equations. SIAM Journal on Numerical Analysis, 19(3):604–613, 1982.
- [28] C. M. Schneider, P. Bressler, P. Schuster, J. Kirschner, J. J. de Miguel, and R. Miranda. Curie temperature of ultrathin films of fcc-cobalt epitaxially grown on atomically flat cu(100) surfaces. *Physical Review Letters*, 64:1059–1062, 1990.
- [29] L. Sun, P. C. Searson, and C. L. Chien. Finite-size effects in nickel nanowire arrays. *Physical review B*, 61(10):6463(4), 2000.
- [30] A. Vansteenkiste, J. Leliaert, M. Dvornik, M. Helsen, F. Garcia-Sanchez, and B. Van Waeyenberge. The design and verification of MuMax3. AIP Advances, 4:107133, 2014.
- [31] J. Wang, W. Wu, F. Zhao, and G.-M. Zhao. Finite-size scaling behavior and intrinsic critical exponents of nickel: Comparison with the three-dimensional Heisenberg model. *Physical Review* B, 84:174440, 2011.
- [32] C. Yang and Q. Jiang. Size and interface effects on critical temperatures of ferromagnetic, ferroelectric and superconductive nanocrystals. *Acta Materialia*, 53(11):3305–3311, 2005.
- [33] R. Zhang and R. F. Willis. Thickness-Dependent Curie Temperatures of Ultrathin Magnetic Films: Effect of the Range of Spin-Spin Interactions. *Physical Review Letters*, 86:2665–2668, 2001.

CLÉMENTINE COURTÈS Université de Strasbourg & Inria Nancy Grand Est CNRS, IRMA UMR 7501, 7 rue René Descartes, 67084 Strasbourg, France clementine.courtes@unistra.fr

> MATTHIEU BOILEAU CNRS & Inria Nancy Grand Est CNRS, IRMA UMR 7501, 67084 Strasbourg, France matthieu.boileau@math.unistra.fr

RAPHAËL CÔTE Université de Strasbourg & University of Strasbourg Institute for Advanced Study CNRS, IRMA UMR 7501, 7 rue René Descartes, 67084 Strasbourg, France raphael.cote@unistra.fr

PAUL-ANTOINE HERVIEUX Université de Strasbourg CNRS, Institut de Physique et Chimie des Matériaux de Strasbourg, UMR 7504 F-67000 Strasbourg, France paul-antoine.hervieux@ipcms.unistra.fr

GIOVANNI MANFREDI Université de Strasbourg CNRS, Institut de Physique et Chimie des Matériaux de Strasbourg, UMR 7504 F-67000 Strasbourg, France giovanni.manfredi@ipcms.unistra.fr